

Lawrence Berkeley National Laboratory

Recent Work

Title

The Reduction of the Critical Current Under Transverse Pressure in a New TWCA MJR Cabled Conductor

Permalink

<https://escholarship.org/uc/item/6wb4n9g9>

Authors

Oort, J. Van
Scanlan, R.M.
Kate, H.H.J. Ten

Publication Date

1993-01-04

**THE REDUCTION OF THE CRITICAL CURRENT UNDER TRANSVERSE
PRESSURE IN A NEW TWCA MJR CABLED CONDUCTOR***

Johannes M. van Oort¹, Ronald M. Scanlan¹, Huub W. Weijers²,
and Herman H.J. ten Kate²

¹Lawrence Berkeley Laboratory
AFRD, Superconducting Magnet Group
1, Cyclotron Road
Berkeley, CA 94720, USA

²Applied Superconductivity Center
University of Twente, Faculty of Applied Physics
P.O. Box 217
7500 AE Enschede, The Netherlands

ABSTRACT

The degradation of the critical current of several impregnated and insulated Rutherford type Nb₃Sn cables is investigated under an applied transverse load and magnetic field. The cables are made of a new TWCA modified jelly-roll strand material which has been optimized for high critical current. The cables have various keystone angles and compaction factors and the dependency of the degradation on these parameters is described. The voltage-current characteristics are determined for the magnetic field ranging from 5 to 11 T and pressure up to 250 MPa. A micro-analysis of the strands is performed before and after the tests to determine possible damage to the filaments. It is found that the initial degradation and subsequent sensitivity to transverse pressure shows a strong dependence on the compaction at the narrow edge during cabling. For a cable in which the strands are deformed by 33 %, an initial degradation due to cabling is found to be 67 %, with a relative degradation of 25 % at 150 MPa. For a rectangular cable with a deformation of only 11 %, the initial damage is less than 2 %, with 3 % degradation at 150 MPa. Moreover, the heavily compacted cables tend to show irreversible damage, whereas the less compacted cables show a full recovery.

* This work was supported by the Director, Office of Energy Research, Office of High Energy and Nuclear Physics, High Energy Physics Division, U.S. Department of Energy, under contract No. DE-AC03-76SF0098.